

Model: RIVEN BROWN ANTISLIP RC 29,5X120(A)

Codes: 100222606 - C279014251

Water absorption: Bla - Porcelanico (E<=0.1%)

Thickness: 25/32" approx.

Family: RIVEN

Tone variations: V3

Finish: MATTE



DIMENSIONAL FEATURES

Thickness	25/32" approx	
Width	11 5/8" approx	
Length	47 1/4" approx	
Length and width deviation	Below 0.15%	<=0.5%*
Side straightness deviation	Below 0.15%	<=0.5%*
Squareness deviation	Below 0.15%	<=0.6%*
Surface flatness deviation	Below 0.15%	<=0.5%*
Thickness tolerance	5 DMM	

MECHANICAL FEATURES

Breaking strength	>404.82 LBF	>292LBF*
Abrasion resistance	PEI 3	
Crack resistance	3	

HYGIENIC FEATURES

Stain resistance	Class 5. Easy cleaning with water	CLASE 3 Min.*
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	CLASE B Min.*

ANTI-SLIP VALUE

Friction (dry)	0.89	
Friction (wet)	0.85	
Slip resistance (ramp)	R11-B	
Slip resistance (pendulum-dry)	>65	
4s	DRY>36-LOW WET>36-LOW	

SCOPE OF USE

Technical code-1	Use on heavy traffic floors	
------------------	-----------------------------	--

PACKING

Boxes	7.62 SQF/CS	
Pallets	228.63 SQF/PAL	
Units	3.81 SQF/ST	

Certified company



Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.
Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by URBATEK S.A.
In its polished finish, due to high gloss, light reflection can create optical effects that resemble stains. In no case they do not comply with the ISO 13006 product standard.
Being the ceramic material that most resembles natural stone, it can show slight variations in shade, color spots and vein among pieces.

#Refer to section 4 of the support document DB/SUA 3. This material can be installed in public, dry areas with a slope under 6% (it gets the same classification as a Class 1 according to wet pendulum).